

TEST REPORT

Test Report # 23W-001419 Date of Report Issue: February 22, 2023
Date of Sample Received: February 13, 2023 Pages: Page 1 of 18

CLIENT INFORMATION:

Company: Polyconcept GBS
Recipient: Kathy Lu
Recipient Email: kathy.lu@polyconceptgbs.com



SAMPLE INFORMATION:

Description: Graphite 15" Computer Briefcase/Grayson 15" Computer Backpack/Graphite Slim 15" Computer Backpack
Article No.: 3450-56GA/3750-02GY/3450-15CA Purchase Order Number: 2003927/2003925/2003936
Factory No.: 3023 Toy Co./Agency: -
Vendor No.: 10461 Country of Origin: -
Country of Distribution: Canada, United States Labeled Age Grade: -
Quantity Submitted: 2 pcs per style Requested Age Grade: -
Testing Period: 02/15/2023-02/21/2023 Tested Age Grade: -


OVERALL RESULT:

PASS

Please refer to the following pages for test result summary and appropriate notes.

QIMA (HANGZHOU) TESTING CO., LTD.

QIMA (HANGZHOU) TESTING CO., LTD.



Jeremy Xu
Chemical Laboratory Supervisor

Thetis Tang
Textile Laboratory Supervisor



QIMA (Hangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1, No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China
Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method/regulation section(s) tested as described herein.
If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule

<https://www.qima.com/conditions-of-service#decisionRule>.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	California Proposition 65, Total Lead in Paints and Surface Coatings
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	Client's Requirement, Phthalates content
PASS	SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile
PASS	Marking of Imported Goods Order, (C.R.C., c.535), Country of Origin
PASS	19 CFR 134.11, Country of Origin



DETAILED RESULTS:

California Proposition 65, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E1003-09.1
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	3	---	---	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	21	---	---	---	---	90
Conclusion	PASS	---	---	---	---	

Note:
mg/kg =Milligrams per kilogram
LT = Less than
ND = Not detected (Reporting Limit = 15mg/kg)

Remark:
The specification is quoted from client's requirement.



DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+5+6	2+8+19	4	7+13+14	9	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	48	22	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	10+11+29	12	15+17+18	16	20+22+24	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	32	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	21+32	23	25+26+31	27	28	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	30+33	34	---	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	---	---	---	100
Conclusion	PASS	PASS	---	---	---	

Note:
 mg/kg = Milligrams per kilogram
 LT = Less than
 ND = Not detected (Reporting Limit = 15 mg/kg)
 Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:
 The specification is quoted from client's requirement.



QIMA (Hangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1, No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China
 Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.
 Test(s) marked with 'ϕ' was subcontracted to external laboratory.
 The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.
 If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule
<https://www.qima.com/conditions-of-service#decisionRule>.
 This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

DETAILED RESULTS:

Client's Requirement, Phthalates content

Test Method: CPSC-CH-C1001-09.4
 Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		2+8+19	3	10+11+29	12	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	163	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.



DETAILED RESULTS:

Client's Requirement, Phthalates content

Test Method: CPSC-CH-C1001-09.4
 Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		16	21+32	27	30+33	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	469	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.



QIMA (Hangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1, No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China

Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with 'Ø' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule

<https://www.qima.com/conditions-of-service#decisionRule>.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

DETAILED RESULTS:

SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2008

Specimen No.	10				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	<u>Test Specimen Direction</u>		Face Length
Items	Result				Client's requirement
	<u>As Received</u>		<u>After Dry-cleaning and Laundering*</u>		
	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	
(1)	-	DNI	-	DNI	>3.5s
(2)	-	DNI	-	DNI	
(3)	-	DNI	-	DNI	
(4)	-	DNI	-	DNI	
(5)	-	DNI	-	DNI	
(6)	-	DNI	-	DNI	
(7)	-	DNI	-	DNI	
(8)	-	DNI	-	DNI	
(9)	-	DNI	-	DNI	
(10)	-	DNI	-	DNI	
Conclusion	PASS				

* Dry-cleaning / Laundering procedure is according to CAN/CGSB-4.2 No.30.3-94 & CAN/CGSB-4.2 No.58-2004; Machine wash at 50°C and tumble dry on the normal setting.

Burn Code Description:

DNI = Did not ignite;



QIMA (Hangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1, No.1213 Huojia South Road, Puyuan Subdistrict, Binjiang District, Hangzhou, China
 Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.
 If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule

[\[https://www.qima.com/conditions-of-service#decisionRule\]](https://www.qima.com/conditions-of-service#decisionRule).

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

DETAILED RESULTS:

SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2008

Specimen No.	11				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	<u>Test Specimen Direction</u>		Face Length
Items	Result				Client's requirement
	<u>As Received</u>		<u>After Dry-cleaning and Laundering*</u>		
	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	
(1)	-	DNI	-	DNI	>3.5s
(2)	-	DNI	-	DNI	
(3)	-	DNI	-	DNI	
(4)	-	DNI	-	DNI	
(5)	-	DNI	-	DNI	
(6)	-	DNI	-	DNI	
(7)	-	DNI	-	DNI	
(8)	-	DNI	-	DNI	
(9)	-	DNI	-	DNI	
(10)	-	DNI	-	DNI	
Conclusion	PASS				

* Dry-cleaning / Laundering procedure is according to CAN/CGSB-4.2 No.30.3-94 & CAN/CGSB-4.2 No.58-2004; Machine wash at 50°C and tumble dry on the normal setting.

Burn Code Description:

DNI = Did not ignite;



QIMA (Hangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1, No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China
 Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.
 If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule

<https://www.qima.com/conditions-of-service#decisionRule>.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

DETAILED RESULTS:

SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2008

Specimen No.	14				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	<u>Test Specimen Direction</u>		Face Length
Items	Result				Client's requirement
	<u>As Received</u>		<u>After Dry-cleaning and Laundering*</u>		
	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	
(1)	8.9	-	8.8	-	>3.5s
(2)	8.8	-	8.8	-	
(3)	8.8	-	8.8	-	
(4)	8.9	-	8.8	-	
(5)	8.9	-	8.7	-	
(Avg.)	8.9	-	8.8	-	
Conclusion	PASS				

* Dry-cleaning / Laundering procedure is according to CAN/CGSB-4.2 No.30.3-94 & CAN/CGSB-4.2 No.58-2004; Machine wash at 50°C and tumble dry on the normal setting.



DETAILED RESULTS:

SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2008

Specimen No.	17				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	<u>Test Specimen Direction</u>		Face Length
Items	Result				Client's requirement
	<u>As Received</u>		<u>After Dry-cleaning and Laundering*</u>		
	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	
(1)	10.1	-	9.8	-	>3.5s
(2)	10.0	-	9.9	-	
(3)	10.0	-	9.9	-	
(4)	10.0	-	9.9	-	
(5)	10.1	-	9.8	-	
(Avg.)	10.0	-	9.9	-	
Conclusion	PASS				

* Dry-cleaning / Laundering procedure is according to CAN/CGSB-4.2 No.30.3-94 & CAN/CGSB-4.2 No.58-2004; Machine wash at 50°C and tumble dry on the normal setting.



DETAILED RESULTS:

SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2008

Specimen No.	25				Face Length
Preliminary Tests	<u>Fabric Surface</u>	Smooth	<u>Test Specimen Direction</u>		
Items	Result				Client's requirement
	<u>As Received</u>		<u>After Dry-cleaning and Laundering*</u>		
	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	
(1)	-	IBE	-	IBE	>3.5s
(2)	-	IBE	-	IBE	
(3)	-	IBE	-	IBE	
(4)	-	IBE	-	IBE	
(5)	-	IBE	-	IBE	
(6)	-	IBE	-	IBE	
(7)	-	IBE	-	IBE	
(8)	-	IBE	-	IBE	
(9)	-	IBE	-	IBE	
(10)	-	IBE	-	IBE	
Conclusion	PASS				

* Dry-cleaning / Laundering procedure is according to CAN/CGSB-4.2 No.30.3-94 & CAN/CGSB-4.2 No.58-2004; Machine wash at 50°C and tumble dry on the normal setting.

Burn Code Description:

IBE = Ignited but extinguished;



DETAILED RESULTS:

SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2008

Specimen No.	29				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	<u>Test Specimen Direction</u>		Face Length
Items	Result				Client's requirement
	<u>As Received</u>		<u>After Dry-cleaning and Laundering*</u>		
	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	
(1)	-	DNI	-	DNI	>3.5s
(2)	-	DNI	-	DNI	
(3)	-	DNI	-	DNI	
(4)	-	DNI	-	DNI	
(5)	-	DNI	-	DNI	
(6)	-	DNI	-	DNI	
(7)	-	DNI	-	DNI	
(8)	-	DNI	-	DNI	
(9)	-	DNI	-	DNI	
(10)	-	DNI	-	DNI	
Conclusion	PASS				

* Dry-cleaning / Laundering procedure is according to CAN/CGSB-4.2 No.30.3-94 & CAN/CGSB-4.2 No.58-2004; Machine wash at 50°C and tumble dry on the normal setting.

Burn Code Description:

DNI = Did not ignite;



DETAILED RESULTS:

SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2008

Specimen No.	30				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	<u>Test Specimen Direction</u>		Face Length
Items	Result				Client's requirement
	<u>As Received</u>		<u>After Dry-cleaning and Laundering*</u>		
	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	
(1)	-	DNI	-	DNI	>3.5s
(2)	-	DNI	-	DNI	
(3)	-	DNI	-	DNI	
(4)	-	DNI	-	DNI	
(5)	-	DNI	-	DNI	
(6)	-	DNI	-	DNI	
(7)	-	DNI	-	DNI	
(8)	-	DNI	-	DNI	
(9)	-	DNI	-	DNI	
(10)	-	DNI	-	DNI	
Conclusion	PASS				

* Dry-cleaning / Laundering procedure is according to CAN/CGSB-4.2 No.30.3-94 & CAN/CGSB-4.2 No.58-2004; Machine wash at 50°C and tumble dry on the normal setting.

Burn Code Description:

DNI = Did not ignite;



DETAILED RESULTS:

SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2008

Specimen No.	34				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	<u>Test Specimen Direction</u>		Face Length
Items	Result				Client's requirement
	<u>As Received</u>		<u>After Dry-cleaning and Laundering*</u>		
	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	
(1)	9.9	-	9.6	-	>3.5s
(2)	9.8	-	9.7	-	
(3)	9.9	-	9.7	-	
(4)	9.9	-	9.9	-	
(5)	9.8	-	9.5	-	
(Avg.)	9.9	-	9.7	-	
Conclusion	PASS				

* Dry-cleaning / Laundering procedure is according to CAN/CGSB-4.2 No.30.3-94 & CAN/CGSB-4.2 No.58-2004; Machine wash at 50°C and tumble dry on the normal setting.



QIMA (Hangzhou) Testing Co., Ltd. ♦ Room 401,4-5/F, Building 1, No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China
 Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158.
 Test(s) marked with 'φ' was subcontracted to external laboratory.
 The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.
 If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule
<https://www.qima.com/conditions-of-service#decisionRule>.
 This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

DETAILED RESULTS:

Marking of Imported Goods Order, (C.R.C., c.535), Country of Origin

Test Parameters	Observation
Goods imported into Canada shall be marked, stamped, branded or labelled in legible English or French words, in a conspicuous place that shall not be covered or obscured by any subsequent attachments or arrangements, so as to indicate the country of origin. It shall be as nearly indelible and permanent as the nature of the goods will permit.	Country of Origin Markings
Conclusion	PASS

19 CFR 134.11, Country of Origin

Test Parameters	Observation	Conclusion
Country of Origin	Present on product and is visible to the consumer at the point of sale.	PASS



SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Black textile	Zipper cloth (3450-56GA /3450-15CA)
2	Black plastic	Zipper teeth (3450-56GA /3450-15CA)
3	Black coating	Zipper head (3450-56GA/3450-15CA)
4	Silvery metal	Zipper head (3450-56GA/3450-15CA)
5	Black textile	Zipper puller string (3450-56GA/3450-15CA)/inner pocket edge (3750-02GY)
6	Black textile	Handle (3450-56GA)/straps edge/adjustable straps (3450-15CA)/handle/straps edge/adjustable straps (3750-02GY)
7	Black textile	Straps/front inner pocket edge (3450-56GA)
8	Black plastic	Buckle/buckle base/adjustable buckle/fixed button (3450-56GA)/Press button/adjustable buckle/buckle/buckle base (3450-15CA)/adjustable buckle (3750-02GY)
9	Silvery metal	Buckle push rod (3450-56GA)
10	Black coated black textile	Base/front pocket edge/back (3450-56GA)/base/front pocket edge (3450-15CA)/front pocket edge (3750-02GY)
11	Black coated grey textile	Front (3450-56GA)/main body/straps (3450-15CA)
12	Black synthetic leather	Front logo (3450-56GA/3450-15CA)
13	Black non-woven textile	Inner edge (all styles)
14	Black textile	Lining (3450-56GA)
15	Black hole mesh textile	Front inner pocket (3450-56GA /3450-15CA)
16	Black/red coated white label	Label (all styles)
17	Grey textile	Lining/side pocket edge (3450-15CA)
18	Black textile	Velcro loop (3450-15CA)
19	Black plastic	Velcro hook (3450-15CA)
20	Black textile	Elastic (3450-15CA)
21	Black soft plastic	Elastic (3450-15CA)



QIMA (Hangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1, No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China

Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method/regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule

[\[https://www.qima.com/conditions-of-service#decisionRule\]](https://www.qima.com/conditions-of-service#decisionRule).

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
22	Black textile	Inner pocket belt of front (3450-15CA)
23	Silvery metal	Eyelet/eyelet base (3450-15CA)
24	Black textile	Drawstring (3450-15CA)
25	Black mesh textile	Back/straps back (3450-15CA)
26	Grey textile	Zipper cloth (3750-02GY)
27	Grey plastic	Zipper teeth (3750-02GY)
28	Silvery metal	Zipper head (3750-02GY)
29	Grey coated grey textile	Main body/straps/zipper puller string (3750-02GY)
30	Grey coated grey textile	Back (3750-02GY)
31	Grey mesh textile	Straps back (3750-02GY)
32	Black soft plastic	Front logo (3750-02GY)
33	Black coated black/grey textile	Front pocket base (3750-02GY)
34	Navy/light grey textile	Lining/front lining (3750-02GY)



QIMA (Hangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1, No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China

Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with 'Ø' was subcontracted to external laboratory.


The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule

[\[https://www.qima.com/conditions-of-service#decisionRule\]](https://www.qima.com/conditions-of-service#decisionRule).

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

SAMPLE PHOTO:



-End Report-

