

## TEST REPORT

Test Report # 21W-022956 Date of Report Issue: September 30, 2021  
Date of Sample Received: September 23, 2021 Pages: Page 1 of 17

### CLIENT INFORMATION:

Company: Polyconcept GBS  
Recipient: kathy lu  
Recipient Email: kathy.lu@polyconceptgbs.com



### SAMPLE INFORMATION:

Description: Angus 12oz Ceramic Mug  
Article No.: SM-6943BK/WH/NY/GY Purchase Order Number: M000024348  
Factory No.: 12331 Toy Co./Agency: -  
Vendor No.: 11236 Country of Origin: China  
Country of Distribution: United States Labeled Age Grade: -  
Quantity Submitted: 13 pcs per color Requested Age Grade: -  
Testing Period: 09/23/2021-09/30/2021 Tested Age Grade: -

### OVERALL RESULT:

 **PASS**

Please refer to the following pages for test result summary and appropriate notes.

QIMA (HANGZHOU) TESTING CO., LTD.



Jeremy Xu  
Chemical Laboratory Supervisor



### TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior
PASS	Canadian Glazed Ceramics and Glassware Regulations SOR/2016-175, Leachable Lead and Cadmium from Ceramics and Glassware – Interior
PASS	California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior



**DETAILED RESULTS:**

**California Proposition 65, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)  
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	6	7	8	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	21	24	22	ND	---	<b>100</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	---	

*Note:*

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

*Remark:*

The specification is quoted from client's requirement.



**DETAILED RESULTS:**

**FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2016)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1-A	1-B	1-C	1-D	1-E	1-F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	380	380	380	380	380	380		
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	NA	

*Note:*

- mL = Millilitres
- mg/L (Milligrams per litre) = ppm (Parts per million)
- NA = Not applicable
- LT = Less than
- ND = Not detected (Reporting Limit: Pb = 0.1 mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	3.0	0.5
	Large Hollowware (Any of 6)	1.0	0.25
	Small Hollowware (Any of 6)	2.0	0.5
	Pitchers (Any of 6)	0.5	0.25



**DETAILED RESULTS:**

**FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2016)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2-A	2-B	2-C	2-D	2-E	2-F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	380	380	380	380	380	380		
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	NA	

*Note:*

- mL = Millilitres
- mg/L (Milligrams per litre) = ppm (Parts per million)
- NA = Not applicable
- LT = Less than
- ND = Not detected (Reporting Limit: Pb = 0.1 mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	3.0	0.5
	Large Hollowware (Any of 6)	1.0	0.25
	Small Hollowware (Any of 6)	2.0	0.5
	Pitchers (Any of 6)	0.5	0.25



**DETAILED RESULTS:**

**FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2016)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	3-A	3-B	3-C	3-D	3-E	3-F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	380	380	380	380	380	380		
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	NA	

*Note:*

- mL = Millilitres
- mg/L (Milligrams per litre) = ppm (Parts per million)
- NA = Not applicable
- LT = Less than
- ND = Not detected (Reporting Limit: Pb = 0.1 mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	3.0	0.5
	Large Hollowware (Any of 6)	1.0	0.25
	Small Hollowware (Any of 6)	2.0	0.5
	Pitchers (Any of 6)	0.5	0.25



**DETAILED RESULTS:**

**FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2016)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4-A	4-B	4-C	4-D	4-E	4-F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	380	380	380	380	380	380		
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	NA	

*Note:*

mL = Millilitres  
 mg/L (Milligrams per litre) = ppm (Parts per million)  
 NA = Not applicable  
 LT = Less than  
 ND = Not detected (Reporting Limit: Pb = 0.1 mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	3.0	0.5
	Large Hollowware (Any of 6)	1.0	0.25
	Small Hollowware (Any of 6)	2.0	0.5
	Pitchers (Any of 6)	0.5	0.25



**DETAILED RESULTS:**

**Canadian Glazed Ceramics and Glassware Regulations SOR/2016-175, Leachable Lead and Cadmium from Ceramics and Glassware – Interior**

Test Method: ISO 6486-1:2019

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1-A	1-B	1-C	1-D	1-E	1-F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	380	380	380	380	380	380	
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.5</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.50</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

*Note:*

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.2mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Any of 6)	<b>0.5</b>	<b>0.50</b>
	Flatware (Any of 6)	<b>3.0</b>	<b>0.50</b>
	Large Hollowware (Any of 6)	<b>1.0</b>	<b>0.25</b>
	Small Hollowware (Any of 6)	<b>2.0</b>	<b>0.50</b>
	Pitchers (Any of 6)	<b>0.5</b>	<b>0.25</b>





**DETAILED RESULTS:**

**Canadian Glazed Ceramics and Glassware Regulations SOR/2016-175, Leachable Lead and Cadmium from Ceramics and Glassware – Interior**

Test Method: ISO 6486-1:2019

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2-A	2-B	2-C	2-D	2-E	2-F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	380	380	380	380	380	380	
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.5</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.50</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

*Note:*

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.2mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Any of 6)	<b>0.5</b>	<b>0.50</b>
	Flatware (Any of 6)	<b>3.0</b>	<b>0.50</b>
	Large Hollowware (Any of 6)	<b>1.0</b>	<b>0.25</b>
	Small Hollowware (Any of 6)	<b>2.0</b>	<b>0.50</b>
	Pitchers (Any of 6)	<b>0.5</b>	<b>0.25</b>



**DETAILED RESULTS:**

**Canadian Glazed Ceramics and Glassware Regulations SOR/2016-175, Leachable Lead and Cadmium from Ceramics and Glassware – Interior**

Test Method: ISO 6486-1:2019

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	3-A	3-B	3-C	3-D	3-E	3-F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	380	380	380	380	380	380	
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.5</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.50</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

*Note:*

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.2mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Any of 6)	<b>0.5</b>	<b>0.50</b>
	Flatware (Any of 6)	<b>3.0</b>	<b>0.50</b>
	Large Hollowware (Any of 6)	<b>1.0</b>	<b>0.25</b>
	Small Hollowware (Any of 6)	<b>2.0</b>	<b>0.50</b>
	Pitchers (Any of 6)	<b>0.5</b>	<b>0.25</b>



**DETAILED RESULTS:**

**Canadian Glazed Ceramics and Glassware Regulations SOR/2016-175, Leachable Lead and Cadmium from Ceramics and Glassware – Interior**

Test Method: ISO 6486-1:2019

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4-A	4-B	4-C	4-D	4-E	4-F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	380	380	380	380	380	380	
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.5</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.50</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

*Note:*

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.2mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Any of 6)	<b>0.5</b>	<b>0.50</b>
	Flatware (Any of 6)	<b>3.0</b>	<b>0.50</b>
	Large Hollowware (Any of 6)	<b>1.0</b>	<b>0.25</b>
	Small Hollowware (Any of 6)	<b>2.0</b>	<b>0.50</b>
	Pitchers (Any of 6)	<b>0.5</b>	<b>0.25</b>



**DETAILED RESULTS:**

**California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2016)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1-A	1-B	1-C	1-D	1-E	1-F	1-G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	380	380	380	380	380	380	380
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
<b>Conclusion</b>							

Specimen No.	1-H	1-I	1-J	1-K	1-L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	380	380	380	380	380		
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.100</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.049</b>
<b>Conclusion</b>						PASS	

**Note:**

- mL = Millilitres
- mg/L (Milligrams per litre) = ppm (Parts per million)
- NA = Not applicable
- LT = Less than
- ND = Not detected (Reporting Limit: Pb = 0.1 mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Flatware (Average of 12)	<b>0.226</b>	<b>0.189</b>
	Large Hollowware (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Small Hollowware (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Pitchers (Average of 12)	<b>0.100</b>	<b>0.049</b>



**DETAILED RESULTS:**

**California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2016)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2-A	2-B	2-C	2-D	2-E	2-F	2-G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	380	380	380	380	380	380	380
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
<b>Conclusion</b>							

Specimen No.	2-H	2-I	2-J	2-K	2-L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	380	380	380	380	380		
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.100</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.049</b>
<b>Conclusion</b>						PASS	

**Note:**

- mL = Millilitres
- mg/L (Milligrams per litre) = ppm (Parts per million)
- NA = Not applicable
- LT = Less than
- ND = Not detected (Reporting Limit: Pb = 0.1 mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Flatware (Average of 12)	<b>0.226</b>	<b>0.189</b>
	Large Hollowware (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Small Hollowware (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Pitchers (Average of 12)	<b>0.100</b>	<b>0.049</b>



Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein. If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

**DETAILED RESULTS:**

**California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2016)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	3-A	3-B	3-C	3-D	3-E	3-F	3-G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	380	380	380	380	380	380	380
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
<b>Conclusion</b>							

Specimen No.	3-H	3-I	3-J	3-K	3-L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	380	380	380	380	380		
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.100</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.049</b>
<b>Conclusion</b>						PASS	

**Note:**

- mL = Millilitres
- mg/L (Milligrams per litre) = ppm (Parts per million)
- NA = Not applicable
- LT = Less than
- ND = Not detected (Reporting Limit: Pb = 0.1 mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Flatware (Average of 12)	<b>0.226</b>	<b>0.189</b>
	Large Hollowware (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Small Hollowware (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Pitchers (Average of 12)	<b>0.100</b>	<b>0.049</b>



Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein. If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

**DETAILED RESULTS:**

**California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2016)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4-A	4-B	4-C	4-D	4-E	4-F	4-G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	380	380	380	380	380	380	380
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
<b>Conclusion</b>							

Specimen No.	4-H	4-I	4-J	4-K	4-L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	380	380	380	380	380		
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.100</b>
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.049</b>
<b>Conclusion</b>						PASS	

**Note:**

- mL = Millilitres
- mg/L (Milligrams per litre) = ppm (Parts per million)
- NA = Not applicable
- LT = Less than
- ND = Not detected (Reporting Limit: Pb = 0.1 mg/L; Cd = 0.02 mg/L)

Category		Leachable Pb (mg/L)	Leachable Cd (mg/L)
X	Cups and Mugs (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Flatware (Average of 12)	<b>0.226</b>	<b>0.189</b>
	Large Hollowware (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Small Hollowware (Average of 12)	<b>0.100</b>	<b>0.049</b>
	Pitchers (Average of 12)	<b>0.100</b>	<b>0.049</b>



Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein. If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Black printed white ceramic	Interior (black style)
2	Navy printed white ceramic	Interior (navy style)
3	Grey printed white ceramic	Interior (grey style)
4	White ceramic	Interior (white style)
5	Black printed white ceramic	Main body (black style)
6	Navy printed white ceramic	Main body (navy style)
7	Grey printed white ceramic	Main body (grey style)
8	White ceramic	Main body (white style)



QIMA (HANGZHOU) TESTING CO., LTD. ♦ 4-5/F A2 BLDG NO. 1213 HUOJU SOUTH ROAD PUYAN STREET BINJIANG DISTRICT HANGZHOU CHINA

♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.



**SAMPLE PHOTO:**



-End Report-

