



**BUREAU
VERITAS**

TEST REPORT

C.C: ZIBO DIZHE INTERNATIONAL TRADING CO., LTD
ADDRESS: 113#ZHONGRUN ROAD, 412# ROOM, FUSHAN BUILDING, ZIBO CITY

LAB NO.: (9021)320-0122
DATE IN: NOV. 16, 2021
DATE MODIFIED: /
DATE OUT: NOV. 23, 2021
NO. OF WORKING DAYS: 6
PAGE 1 OF 11

OVERALL RATING	
SATISFACTORY	_____ X _____
UNSATISFACTORY	_____
DATA	_____

Vendor:	ZIBO DIZHE INTERNATIONAL TRADING CO., LTD	Agent:	/
Raw Material Supplier:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	9987-00WBL, 9987-00BKW, 9987-00BKRE, 9987-00BKBL
Sample Description:	CERAMIC MUG	SKU#:	9987-00WBL, 9987-00BKW, 9987-00BKRE, 9987-00BKBL
Color:	MULTIROW	Country of Origin:	CHINA
Buyer Name:	BULLET	Submitted Size:	/
Submitted Amount:	/	End Use:	/
Country of Distribution	USA	Others:	/

Product Category:	/
Test Requested:	SEE BELOW
Previous Report No.:	/

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
Extractable Lead and Cadmium Content in Interior of Ceramicware - United States Food and Drug Administration (FDA) Compliance Policy Guides (CPG), Sections 545.400 (CPG 7117.06) and 545.450 (CPG 7117.07)	X			
Extractable Lead and Cadmium in Ceramicware- California Proposition 65	X			
Extractable Lead and Cadmium in Ceramic and Glass - CCPSA Glazed Ceramics and Glassware Regulations -SOR/2016-175 Sec.2	X			
Extractable Lead and Cadmium Content from External Decoration in Lip and Rim Area - California Proposition 65	X			
Extractable Lead and Cadmium Content from External Decoration in Lip and Rim Area - Society of Glass and Ceramic Decorators (SGCD)	X			
Extractable Lead and Cadmium in Lip and Rim - Glazed Ceramic and Glassware Regulation - SOR/2016-175 Sec.3	X			
Total Lead Content in Substrate - United States Consumer Product Safety Improvement Act (CPSIA) Section 101(a)(2)	X			

Remark:

The client specifies the test method and requirement.

BVCPS (SHANGHAI)-QINGDAO BRANCH CONTACT INFORMATION FOR THIS REPORT

Enquiry and invoicing:

Wendy Huang 86-533-7868187 wendy.huang@bureauveritas.com
Sunnee Li 86-533-7868185 sunnee.li@bureauveritas.com

Bureau Veritas
Consumer Products Services (Shanghai)-Qingdao Branch



Anderson Zhang
Qingdao Hardline Reporting Manager

TEST RESULT

Test Item(s)	Item / Component Description(s)	Location(s)	Style(s)
I001	Ceramicware	-	A
I002	Ceramicware	-	B
I003	Ceramicware	-	C
I004	Ceramicware	-	D

1.Extractable Lead and Cadmium Content in Interior of Glassware - United States Food and Drug Administration (FDA) Compliance Policy Guides (CPG), Sections 545.400 (CPG 7117.06) and 545.450 (CPG 7117.07)

Test Method : AOAC 973.32 (2007) / ASTM C738-94 (R2020)

Extractable Element(s)		Pb	Cd
Maximum Allowable Limit (mg/L) (Average of 6 trials)	Type I – Flatware	3.0	0.5
	Type II - Small hollowware	2.0	0.5
	Type III - Large hollowware	1.0	0.25
	Type IV - Cup and mug	0.5	0.5*
	Type V - Small pitcher	0.5	0.5*
	Type VI - Large pitcher	0.5	0.25^

		Result			
-		I001			
Test Item(s)		IV			
Type					
Parameter	Internal Depth	Leaching Volume	Lead (Pb)	Cadmium (Cd)	
Unit	Mm	mL	mg/L	mg/L	
Test Sample(s) / Trial(s)	-	-	-	-	
Trial 1	95	450	<0.05	<0.01	
Trial 2	95	450	<0.05	<0.01	
Trial 3	95	450	<0.05	<0.01	
Trial 4	95	450	<0.05	<0.01	
Trial 5	95	450	<0.05	<0.01	
Trial 6	95	450	<0.05	<0.01	
Average	-	-	<0.05	<0.01	
Conclusion		PASS			

		Result			
-		I002			
Test Item(s)		IV			
Type					
Parameter	Internal Depth	Leaching Volume	Lead (Pb)	Cadmium (Cd)	
Unit	Mm	mL	mg/L	mg/L	
Test Sample(s) / Trial(s)	-	-	-	-	
Trial 1	95	450	<0.05	<0.01	
Trial 2	95	450	<0.05	<0.01	
Trial 3	95	450	<0.05	<0.01	
Trial 4	95	450	<0.05	<0.01	

Trial 5	95	450	<0.05	<0.01
Trial 6	95	450	<0.05	<0.01
Average	-	-	<0.05	<0.01
Conclusion		PASS		

-	Result			
Test Item(s)	I003			
Type	IV			
Parameter	Internal Depth	Leaching Volume	Lead (Pb)	Cadmium (Cd)
Unit	Mm	mL	mg/L	mg/L
Test Sample(s) / Trial(s)	-	-	-	-
Trial 1	95	450	<0.05	<0.01
Trial 2	95	450	<0.05	<0.01
Trial 3	95	450	<0.05	<0.01
Trial 4	95	450	<0.05	<0.01
Trial 5	95	450	<0.05	<0.01
Trial 6	95	450	<0.05	<0.01
Average	-	-	<0.05	<0.01
Conclusion		PASS		

Note/Key : ND = Not detected “<” = less than mm = millimeter(s)
 mg/L = milligram(s) per liter = ppm = part(s) per million mL = milliliter(s)
 Detection Limit (mg/L) : Pb 0.050; Cd 0.010

Remark:

- Product(s) with extractable lead content and (or) extractable cadmium content exceeding the corresponding maximum allowable limit has (have) to comply with the warning utilization requirement.

2. Extractable Lead and Cadmium in Ceramicware- California Proposition 65

Test Method : AOAC 973.32 (2007) / ASTM C738-94 (R2020)

Extractable Element(s)		Pb	Cd
Maximum Allowable Limit (mg/L) (Any 1 of 12 trials)	Type I – Flatware	0.226	1.853
	Type II - Small hollowware	0.100	0.189
	Type III - Large hollowware	0.100	0.049

-	Result			
Test Item(s)	I001			
Type	II			
Parameter	Internal Depth	Leaching Volume	Lead (Pb)	Cadmium (Cd)
Unit	Mm	mL	mg/L	mg/L
Test Sample(s) / Trial(s)	-	-	-	-
Trial 1	95	450	ND	ND
Trial 2	95	450	ND	ND
Trial 3	95	450	ND	ND
Trial 4	95	450	ND	ND
Trial 5	95	450	ND	ND
Trial 6	95	450	ND	ND
Trial 7	95	450	ND	ND
Trial 8	95	450	ND	ND

- Product(s) with extractable lead and (or) extractable cadmium content exceeding the corresponding maximum allowable limit has (have) to comply with the warning utilization requirement.
- Apart from these extractable lead and cadmium requirements of California Proposition 65 or California Health and Safety Code, Section 25249.5, product(s) has (have) to comply with the extractable lead and cadmium requirements of United States Food and Drug Administration (FDA) Compliance Policy Guides (CPG), Sections 545.400 (CPG 7117.06) and 545.450 (CPG 7117.07).

3. Extractable Lead and Cadmium in Ceramic and Glass - CCPSA Glazed Ceramics and Glassware Regulations

-SOR/2016-175 Sec.2

Test Method : ISO 6486-1:1999

Extractable Element(s)		Pb	Cd
Maximum Allowable Limit (mg/L) (Average of 6 trials)	Type I – Flatware	3.0	0.5
	Type II - Small hollowware	2.0	0.5
	Type III - Large hollowware	1.0	0.25
	Type IV - Cup and mug	0.5	0.5
	Type V - Pitcher	0.5	0.25

		Result		
Test Item(s)		I001		
Type		IV		
Parameter	Internal Depth	Leaching Volume	Lead (Pb)	Cadmium (Cd)
Unit	Mm	mL	mg/L	mg/L
Test Sample(s) / Trial(s)	-	-	-	-
Trial 1	95	450	<0.05	<0.01
Trial 2	95	450	<0.05	<0.01
Trial 3	95	450	<0.05	<0.01
Trial 4	95	450	<0.05	<0.01
Trial 5	95	450	<0.05	<0.01
Trial 6	95	450	<0.05	<0.01
Average	-	-	<0.05	<0.01
Conclusion		PASS		

		Result		
Test Item(s)		I002		
Type		IV		
Parameter	Internal Depth	Leaching Volume	Lead (Pb)	Cadmium (Cd)
Unit	Mm	mL	mg/L	mg/L
Test Sample(s) / Trial(s)	-	-	-	-
Trial 1	95	450	<0.05	<0.01
Trial 2	95	450	<0.05	<0.01
Trial 3	95	450	<0.05	<0.01
Trial 4	95	450	<0.05	<0.01
Trial 5	95	450	<0.05	<0.01
Trial 6	95	450	<0.05	<0.01
Average	-	-	<0.05	<0.01
Conclusion		PASS		

-	Result			
Test Item(s)	I003			
Type	IV			
Parameter	Internal Depth	Leaching Volume	Lead (Pb)	Cadmium (Cd)
Unit	Mm	mL	mg/L	mg/L
Test Sample(s) / Trial(s)	-	-	-	-
Trial 1	95	450	<0.05	<0.01
Trial 2	95	450	<0.05	<0.01
Trial 3	95	450	<0.05	<0.01
Trial 4	95	450	<0.05	<0.01
Trial 5	95	450	<0.05	<0.01
Trial 6	95	450	<0.05	<0.01
Average	-	-	<0.05	<0.01
Conclusion	PASS			

Note/Key : ND = Not detected “<” = less than mm = millimeter(s)
 mg/L = milligram(s) per liter = ppm = part(s) per million mL = milliliter(s)
 Detection Limit (mg/L) : Pb 0.050; Cd 0.010

Remark:

- Product(s) with extractable lead content and (or) extractable cadmium content exceeding the corresponding maximum allowable limit has (have) to comply with the warning utilization requirement.

4. Extractable Lead and Cadmium Content from External Decoration in Lip and Rim Area - California Proposition 65

Test Method : ASTM C927-80(R2019e1)

Extractable Element(s)	Pb	Cd
Maximum Allowable Limit (mg/L) (Any 1 of 6 trials)	0.5	4.0

-	Result			
Test Item(s)	I001			
Type	-			
Parameter	Internal Volume	Leaching Volume	Lead (Pb)	Cadmium (Cd)
Unit	mL	mL	mg/L	mg/L
Test Sample(s) / Trial(s)	-	-	-	-
Trial 1	450	175	<0.05	<0.01
Trial 2	450	175	<0.05	<0.01
Trial 3	450	175	<0.05	<0.01
Trial 4	450	175	<0.05	<0.01
Trial 5	450	175	<0.05	<0.01
Trial 6	450	175	<0.05	<0.01
Conclusion	PASS			

Original Sample



END