

## TEST REPORT

Test Report # 19H-002304(A1) Date of Report Issue: June 6, 2019  
Date of Sample Received: April 11, 2019 Pages: Page 1 of 70

### CLIENT INFORMATION:

Company: Polyconcept GBS  
Recipient: Jenny Liu  
Recipient Email: Jenny.Liu@polyconceptgbs.com



### SAMPLE INFORMATION:

Description:	Refer to Page 2 to 4	Purchase Order Number:	Refer to Page 2 to 4
Assortment:	-	Toy Co./Agency:	-
Article No.:	Refer to Page 2 to 4	Country of Origin:	China
Vendor Name:	11162	Labeled Age Grade:	-
Country of Distribution:	United States, Canada	Requested Age Grade:	-
Quantity Submitted:	Refer to Page 2 to 4	Tested Age Grade:	-
Testing Period:	04/12/2019 – 05/16/2019 05/23/2019 – 06/04/2019		

### OVERALL RESULT:

 **PASS**

Refer to page 5 for test result summary and appropriate notes.

QIMA Testing (HK) Limited



Loska Yeung Lok Ka  
Assistant Manager, Chemical Laboratory

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 2 of 70

**ARTICLE/ PO NO./ QUANTITY SUBMITTED DETAILED:**

Style description	Article No.	PO No.	Qty.
elleven Traverse Tumbler 16oz	0011-87 BK	1780886	6 pcs
	0011-87 SL	1774812	6 pcs
Copper Vacuum Tumbler with Ceramic Lining 20oz	1625-25 BK	1712479	24 pcs
	1625-25 BL	1712478	24 pcs
	1625-25 SL	1712480	24 pcs
Milo Copper Vacuum Tumbler 20oz	1625-28 BK	1781024	6 pcs
	1625-28 BL	1791518	6 pcs
	1625-28 COP	1712441	6 pcs
	1625-28 RD	1802435	6 pcs
	1625-28 SL	1720545	6 pcs
	1625-28 TQ	1780411	6 pcs
Mega Milo Copper Vacuum Tumbler 30oz	1625-45 BK	1781147	6 pcs
Mega Hugo Copper Vacuum Ins Tmbr	1625-09 BK	1803925	6 pcs
	1625-09 BL	1785355	6 pcs
	1625-09 COP	1718650	6 pcs
	1625-09 GA	1771761	6 pcs
	1625-09 LM	1738274	6 pcs
	1625-09 RD	1749530	6 pcs
	1625-09 SL	1711649	6 pcs
Hugo Copper Vacuum Insulated Tmbr	1624-89 BL	1790274	6 pcs
	1624-89 BK	1788955	6 pcs
	1624-89 GA	1803932	6 pcs
	1624-89 COP	1711624	6 pcs
	1624-89 LM	1803663	6 pcs
	1624-89 RD	1780352	6 pcs
	1624-89 WH	1775900	6 pcs
	1624-89 SL	1761763	6 pcs
Ozzy BPA Free Tritan™ Audio Bottle 25oz	1625-81 RYL	1785804	6 pcs
	1625-81 SM	1792866	6 pcs

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 3 of 70

**ARTICLE/ PO NO./ QUANTITY SUBMITTED DETAILED:**

Style description	Article No.	PO No.	Qty.
Nova Vacuum Coffee and Tea Tumbler 16oz	1625-23 SL	1749532	6 pcs
Grotto Ceramic Mug 16oz	1624-92BK	1803316	24 pcs
	1624-92WH	1792391	24 pcs
Poppi Glass Tumbler 20oz 1625-79=9987-13	9987-13BK	1793091	6 pcs
	9987-13BL	1776894	6 pcs
	9987-13WH	1787900	6 pcs
	9987-13MTGR	1803936	6 pcs
Poppi Lid 1625-79=9987-12	9987-12BK	1788710	6 pcs
	9987-12BL	1776536	6 pcs
	9987-12WH	1792280	6 pcs
	9987-12MTGR	1781572	6 pcs
Spirit Tritan™ Sport Bottle with Glass Liner	1625-74CL	1784209	6 pcs
	1625-74SGL	1777263	6 pcs
	1625-74SM	1777264	6 pcs
Hugo Auto-Seal Copper Vacuum Insulated Bottle	1625-80BK	1789380	6 pcs
	1625-80WH	1787825	6 pcs
	1625-80SL	1788775	6 pcs
Soundwave Copper Vacuum Audio Bottle	1625-93BK	1797910	6 pcs
	1625-93SL	1802926	6 pcs
Supernova Gradient Vac Ins Bottle	1626-43BK	1784600	6 pcs
	1626-43BL	1784599	6 pcs
	1626-43LM	1784595	6 pcs
	1626-43RD	1784598	6 pcs

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 4 of 70

**ARTICLE/ PO NO./ QUANTITY SUBMITTED DETAILED:**

Style description	Article No.	PO No.	Qty.
Hugo Vac Ins Bottle 18oz.	1626-25COP	M000003506	6 pcs
	1626-25BK	1796272	6 pcs
	1626-25BL	1803498	6 pcs
	1626-25GA	1793633	6 pcs
	1626-25LM	1802449	6 pcs
	1626-25RD	M000003506	6 pcs
	1626-25SL	1796565	6 pcs
	1626-25WH	1796579	6 pcs
Hugo Copper Vacuum Insulated Tumbler	1626-07BK	1775070	6 pcs
	1626-07BL	1796561	6 pcs
	1626-07LM	1775067	6 pcs
	1626-07RD	1797257	6 pcs
Hugo Vacuum Insulated Tumbler	1626-24BK	1796594	6 pcs
	1626-24BL	1808384	6 pcs
	1626-24RD	1796162	6 pcs
	1626-24SL	1794815	6 pcs
	1626-24WH	1808403	6 pcs

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 5 of 70

**TEST RESULTS SUMMARY:**

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings
PASS	California Proposition 65, Total Lead in Paints and Surface Coatings
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	California Proposition 65, Total Lead in Glass and Ceramic Materials <sup>#</sup>
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	FDA GRAS Specifications, Total Chromium in Stainless Steel Food Containers <sup>#</sup>
PASS	Client's Requirement, Bisphenol A <sup>#</sup>
PASS	FDA 21 CFR 175.300, Resinous and Polymeric Coatings <sup>#</sup>
PASS	FDA 21 CFR 177.1210, Closures with Sealing Gaskets <sup>#</sup>
PASS	FDA 21 CFR 177.1520, Polypropylene Copolymers
PASS	FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers
PASS	FDA 21 CFR 177.2600, Rubber
PASS	FDA 21 CFR 178.3800, Preservatives for Wood – Pentachlorophenol (PCP)
PASS	FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers
PASS	California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior
PASS	FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior
PASS	Client's Requirement, Leachable Lead & Cadmium from Glassware and Ceramics – Lip & Rim
PASS	Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead in Surface Coating Materials
PASS	Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content
PASS	Canadian Glazed Ceramics and Glassware Regulations SOR/2016-175, Leachable Lead and Cadmium from Ceramics and Glassware – Interior

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 6 of 70

**DETAILED RESULTS:****CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings**

Test Method: CPSC-CH-E-1003-09.1  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5	6+7+8	9+10+11	12+13	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	27	ND	ND	ND	ND	<b>90</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	14	74+75	77+78+79	80+81+82	83+84	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	<b>90</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	130+131	132+133	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	---	---	---	<b>90</b>
<b>Conclusion</b>	PASS	PASS	---	---	---	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 7 of 70

**DETAILED RESULTS:****California Proposition 65, Total Lead in Paints and Surface Coatings**

Test Method: CPSC-CH-E-1003-09.1  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5	6+7+8	9+10+11	12+13	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	27	ND	ND	ND	ND	<b>90</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	14	74+75	77+78+79	80+81+82	83+84	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	<b>90</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	130+131	132+133	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	---	---	---	<b>90</b>
<b>Conclusion</b>	PASS	PASS	---	---	---	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 8 of 70

**DETAILED RESULTS:****California Proposition 65, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	16+17+18	19+20+21	22+23	24+25	26+27+28	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	<b>100</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	29+30+31	32+33	34	36+37	38+39+40	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	<b>100</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	41+42	43+44	53	54	55	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	<b>100</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.





YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 9 of 70

**DETAILED RESULTS:****California Proposition 65, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	56	57	58	85+86	87	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	31	ND	ND	ND	<b>100</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	88	90	94+95	96+97+98	99+100	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	<b>100</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	115	116	117	118	119	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	28	ND	ND	ND	<b>100</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 10 of 70

**DETAILED RESULTS:****California Proposition 65, Total Lead in Glass and Ceramic Materials**

Test Method: In-House Method#  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	125+126	127+128	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	25	---	---	---	<b>100</b>
<b>Conclusion</b>	PASS	PASS	---	---	---	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 11 of 70

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1+2+3	4+5	6+7+8	9+10+11	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	LT 670	LT 720	LT 720	LT 550	<b>1000</b>
Benzyl butyl phthalate (BBP)	85-68-7	LT 670	LT 720	LT 720	LT 550	<b>1000</b>
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	LT 670	LT 720	LT 720	LT 550	<b>1000</b>
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	LT 670	LT 720	LT 720	LT 550	<b>1000</b>
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	LT 670	LT 720	LT 720	LT 550	<b>1000</b>
Di-n-hexyl phthalate (DnHP)	84-75-3	LT 670	LT 720	LT 720	LT 550	<b>1000</b>
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 12 of 70

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		12+13	14	16+17+18	19+20+21	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	LT 710	LT 350	ND	ND	<b>1000</b>
Benzyl butyl phthalate (BBP)	85-68-7	LT 710	LT 350	ND	ND	<b>1000</b>
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	LT 710	LT 350	ND	ND	<b>1000</b>
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	LT 710	LT 350	ND	ND	<b>1000</b>
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	LT 710	LT 350	ND	ND	<b>1000</b>
Di-n-hexyl phthalate (DnHP)	84-75-3	LT 710	LT 350	ND	ND	<b>1000</b>
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 13 of 70

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		22+23	24+25	26+27+28	29+30+31	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 14 of 70

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		32+33	34	36+37	38+39+40	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	<b>1000</b>
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	<b>1000</b>
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	<b>1000</b>
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	<b>1000</b>
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	<b>1000</b>
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	<b>1000</b>
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 15 of 70

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		41+42	43+44	74+75	77+78+79	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	440	LT 580	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	LT 580	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	340	LT 580	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	LT 580	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	LT 580	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	LT 580	1000
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 16 of 70

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		80+81+82	83+84	85+86	87	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	LT 690	LT 420	ND	ND	<b>1000</b>
Benzyl butyl phthalate (BBP)	85-68-7	LT 690	LT 420	ND	ND	<b>1000</b>
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	LT 690	LT 420	ND	ND	<b>1000</b>
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	LT 690	LT 420	ND	ND	<b>1000</b>
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	LT 690	LT 420	ND	ND	<b>1000</b>
Di-n-hexyl phthalate (DnHP)	84-75-3	LT 690	LT 420	ND	ND	<b>1000</b>
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.





YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 17 of 70

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		88	90	94+95	96+97+98	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	<b>1000</b>
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	<b>1000</b>
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	<b>1000</b>
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	<b>1000</b>
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	<b>1000</b>
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	<b>1000</b>
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 18 of 70

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		99+100	130+131	132+133	---	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	<b>1000</b>
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	<b>1000</b>
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	<b>1000</b>
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	<b>1000</b>
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	<b>1000</b>
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	---	<b>1000</b>
<b>Conclusion</b>		PASS	PASS	PASS	---	

**Note:**

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 300 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 19 of 70

**DETAILED RESULTS:****FDA GRAS Specifications, Total Chromium in Stainless Steel Food Containers**

Test Method: In-House Method#  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	52	---	---	---	---	
Test Item	Result (% m/m)	Result (% m/m)	Result (% m/m)	Result (% m/m)	Result (% m/m)	Limit (% m/m)
Total Chromium (Cr)	18.7	---	---	---	---	<b>GT 16</b>
<b>Conclusion</b>	PASS	---	---	---	---	

*Note:*

% m/m = Percent by mass  
 GT = Greater than

*Remark:*

The limit is quoted from ANSI/NSF 51-1997 Section 7.1.2.

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 20 of 70

**DETAILED RESULTS:****Client's Requirement, Bisphenol A**

Test Method: In-House Method#  
 Analytical Method: Liquid Chromatography with Fluorescence Detection

Specimen No.		1	15	17	18	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

Specimen No.		19	20	21	22	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

Specimen No.		23	24	25	41	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

Specimen No.		42	43	44	74	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not Detected (Reporting Limit = 1 ppm)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 21 of 70

**DETAILED RESULTS:****Client's Requirement, Bisphenol A**

Test Method: In-House Method#  
 Analytical Method: Liquid Chromatography with Fluorescence Detection

Specimen No.	91	92	93	98	Limit (ppm)
Test Item CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA) 80-05-7	ND	ND	ND	ND	ND
<b>Conclusion</b>	PASS	PASS	PASS	PASS	

Specimen No.	100	101	---	---	Limit (ppm)
Test Item CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Bisphenol A (BPA) 80-05-7	ND	ND	---	---	ND
<b>Conclusion</b>	PASS	PASS	---	---	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not Detected (Reporting Limit = 1 ppm)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 22 of 70

**DETAILED RESULTS:****FDA 21 CFR 175.300, Resinous and Polymeric Coatings**Test Method: FDA 21 CFR 175.300<sup>#</sup>

Specimen No.			1	---	RL (mg/in <sup>2</sup> )	Limit (mg/in <sup>2</sup> )
Test Item	Test Condition		Result (mg/in <sup>2</sup> )	Result (mg/in <sup>2</sup> )		
	Temp.	Duration				
Distilled water extractive	Fill boiling	Until Cool to 100°F	0.30	---	<b>0.1</b>	<b>18</b>
<b>Conclusion</b>			PASS	---		

Specimen No.			74	---	RL (mg/in <sup>2</sup> )	Limit (mg/in <sup>2</sup> )
Test Item	Test Condition		Result (mg/in <sup>2</sup> )	Result (mg/in <sup>2</sup> )		
	Temp.	Duration				
Distilled water extractive	120°F	24 hours	0.16*	---	<b>0.1</b>	<b>18</b>
<b>Conclusion</b>			PASS	---		

**Note:**

Temp. = Temperature

°F = Degree Fahrenheit

mg/in<sup>2</sup> = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 175.300 (c) (3).

\*The chloroform-soluble extractive analysis was conducted.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 23 of 70

**DETAILED RESULTS:****FDA 21 CFR 177.1210, Closures with Sealing Gaskets**Test Method: FDA 21 CFR 177.1210<sup>#</sup>

Specimen No.			42	43	RL (ppm)	Limit (ppm)
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	Fill boiling	Until Cool to 100°F	ND	21	10	50
<b>Conclusion</b>			PASS	PASS		

Specimen No.			48	49	RL (ppm)	Limit (ppm)
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	Fill boiling	Until Cool to 100°F	ND	ND	10	50
<b>Conclusion</b>			PASS	PASS		

Specimen No.			50	51	RL (ppm)	Limit (ppm)
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	Fill boiling	Until Cool to 100°F	ND	19	10	50
<b>Conclusion</b>			PASS	PASS		

**Note:**

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram foodstuff)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 24 of 70

**DETAILED RESULTS:****FDA 21 CFR 177.1210, Closures with Sealing Gaskets**Test Method: FDA 21 CFR 177.1210<sup>#</sup>

Specimen No.			98	102	RL (ppm)	Limit (ppm)
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	Fill boiling	Until Cool to 100°F	ND	ND	10	50
<b>Conclusion</b>			PASS	PASS		

Specimen No.			103	104	RL (ppm)	Limit (ppm)
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	Fill boiling	Until Cool to 100°F	ND	ND	10	50
<b>Conclusion</b>			PASS	PASS		

**Note:**

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram foodstuff)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.





YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 25 of 70

**DETAILED RESULTS:****FDA 21 CFR 177.1210, Closures with Sealing Gaskets**Test Method: FDA 21 CFR 177.1210<sup>#</sup>

Specimen No.			105	106	RL (ppm)	Limit (ppm)
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	Fill boiling	Until Cool to 100°F	ND	ND	10	50
<b>Conclusion</b>			PASS	PASS		

Specimen No.			134	---	RL (ppm)	Limit (ppm)
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	Fill boiling	Until Cool to 100°F	ND	---	10	50
<b>Conclusion</b>			PASS	---		

**Note:**

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram foodstuff)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 26 of 70

**DETAILED RESULTS:****FDA 21 CFR 177.1210, Closures with Sealing Gaskets**Test Method: FDA 21 CFR 177.1210<sup>#</sup>

Specimen No.			107	108	RL (ppm)	Limit (ppm)
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	120°F	24 hours	ND	ND	10	50
<b>Conclusion</b>			PASS	PASS		

Specimen No.			109	110	RL (ppm)	Limit (ppm)
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	120°F	24 hours	ND	ND	10	50
<b>Conclusion</b>			PASS	PASS		

**Note:**

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram foodstuff)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 27 of 70

**DETAILED RESULTS:****FDA 21 CFR 177.1210, Closures with Sealing Gaskets**Test Method: FDA 21 CFR 177.1210<sup>#</sup>

Specimen No.			46	47	RL (ppm)	Limit (ppm)
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	Fill boiling	Until Cool to 100°F	10	12	<b>10</b>	<b>50</b>
<b>Conclusion</b>			PASS	PASS		

*Note:*

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram foodstuff)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

*Remark:*

The specification is quoted from 21 CFR 177.1210 Table 2 Section 3.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 28 of 70

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			15	17	RL	Limit
Test Item	Temp.	Duration	Result	Result		
Density (g/cc)	NA	NA	0.897	0.893	NA	0.85-1.00
n-Hexane extractive (%)	50°C	2 hours	2.6	2.5	0.4	5.5
Xylene extractive (%)	Reflux	2 hours or until total dissolved	6.7	6.4	1.0	30
<b>Conclusion</b>			PASS	PASS		

Specimen No.			18	19	RL	Limit
Test Item	Temp.	Duration	Result	Result		
Density (g/cc)	NA	NA	0.895	0.894	NA	0.85-1.00
n-Hexane extractive (%)	50°C	2 hours	3.2	1.1	0.4	5.5
Xylene extractive (%)	Reflux	2 hours or until total dissolved	6.7	2.6	1.0	30
<b>Conclusion</b>			PASS	PASS		

**Note:**

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 29 of 70

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			20	21	RL	Limit
Test Item	Temp.	Duration	Result	Result		
Density (g/cc)	NA	NA	0.895	0.893	NA	0.85-1.00
n-Hexane extractive (%)	50°C	2 hours	3.6	3.2	0.4	5.5
Xylene extractive (%)	Reflux	2 hours or until total dissolved	7.1	7.2	1.0	30
<b>Conclusion</b>			PASS	PASS		

**Note:**

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 30 of 70

**DETAILED RESULTS:****FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers**

Test Method: FDA 21 CFR 177.1630

Specimen No.			23	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	250°F	2 hours	0.27	<b>0.1</b>	<b>0.5</b>
n-Heptane extractive (mg/in <sup>2</sup> )	150°F	2 hours	ND	<b>0.1</b>	<b>0.5</b>
<b>Conclusion</b>			PASS		

Specimen No.			24	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	250°F	2 hours	0.20	<b>0.1</b>	<b>0.5</b>
n-Heptane extractive (mg/in <sup>2</sup> )	150°F	2 hours	ND	<b>0.1</b>	<b>0.5</b>
<b>Conclusion</b>			PASS		

Specimen No.			25	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	250°F	2 hours	0.11	<b>0.1</b>	<b>0.5</b>
n-Heptane extractive (mg/in <sup>2</sup> )	150°F	2 hours	0.10	<b>0.1</b>	<b>0.5</b>
<b>Conclusion</b>			PASS		

**Note:**

Temp. = Temperature

°F = Degree Fahrenheit

mg/in<sup>2</sup> = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 177.1630 (f).

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 31 of 70

**DETAILED RESULTS:****FDA 21 CFR 177.2600, Rubber**

Test Method: FDA 21 CFR 177.2600

Specimen No.			111	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	Reflux	First 7 hours	ND	<b>2</b>	<b>20</b>
Distilled water extractive (mg/in <sup>2</sup> )	Reflux	Succeeding 2 hours	ND	<b>0.1</b>	<b>1</b>
<b>Conclusion</b>			PASS		

Specimen No.			112	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	Reflux	First 7 hours	ND	<b>2</b>	<b>20</b>
Distilled water extractive (mg/in <sup>2</sup> )	Reflux	Succeeding 2 hours	ND	<b>0.1</b>	<b>1</b>
<b>Conclusion</b>			PASS		

**Note:**

Temp. = Temperature

mg/in<sup>2</sup> = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 177.2600 (e).

From Client's information, rubber article was intended for repeated use in contact with aqueous food only, therefore n-hexane extractive was not conducted.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 32 of 70

**DETAILED RESULTS:****FDA 21 CFR 177.2600, Rubber**

Test Method: FDA 21 CFR 177.2600

Specimen No.			113	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	Reflux	First 7 hours	ND	<b>2</b>	<b>20</b>
Distilled water extractive (mg/in <sup>2</sup> )	Reflux	Succeeding 2 hours	0.1	<b>0.1</b>	<b>1</b>
<b>Conclusion</b>			PASS		

Specimen No.			114	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	Reflux	First 7 hours	ND	<b>2</b>	<b>20</b>
Distilled water extractive (mg/in <sup>2</sup> )	Reflux	Succeeding 2 hours	0.2	<b>0.1</b>	<b>1</b>
<b>Conclusion</b>			PASS		

**Note:**

Temp. = Temperature

mg/in<sup>2</sup> = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 177.2600 (e).

From Client's information, rubber article was intended for repeated use in contact with aqueous food only, therefore n-hexane extractive was not conducted.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.





YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 33 of 70

**DETAILED RESULTS:****FDA 21 CFR 178.3800, Preservatives for Wood – Pentachlorophenol (PCP)**

Test Method: In-House Method#  
 Analytical Method: Gas Chromatography-Electron Capture Detector

Specimen No.	129	---	---	---	---	<b>Limit (ppm)</b>
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Pentachlorophenol (PCP)	ND	---	---	---	---	<b>50</b>
<b>Conclusion</b>	PASS	---	---	---	---	

*Note:*

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 0.1 ppm)

*Remark:*

The specification is quoted from 21 CFR 178.3800(b).

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 34 of 70

**DETAILED RESULTS:****FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers**

Test Method: FDA 21 CFR 180.22 and 181.32  
 Analytical Method: Headspace-Gas Chromatography with Mass Spectrometry

Acrylonitrile Monomers:

Specimen No.			22	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	120°F	2 hours	ND	<b>0.001</b>	<b>0.003</b>
3% Acetic acid extractive (mg/in <sup>2</sup> )	120°F	2 hours	ND	<b>0.001</b>	<b>0.003</b>
<b>Conclusion</b>			PASS		

*Note:*

Temp. = Temperature

°F = Degree Fahrenheit

mg/in<sup>2</sup> = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

*Remark:*

The specification is quoted from 21 CFR 181.32 (b) (3).

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 35 of 70

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	120A	120B	120C	120D	120E	120F	120G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	590	590	590	590	590	590	590
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
<b>Conclusion</b>							

Specimen No.	120H	120I	120J	120K	120L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	590	590	590	590	590		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.049</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.100</b>
<b>Conclusion</b>						PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 36 of 70

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Flatware (Average of 12)	<b>0.189</b>	<b>0.226</b>
	Large Hollowware (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Small Hollowware (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Pitchers (Average of 12)	<b>0.049</b>	<b>0.100</b>

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 37 of 70

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	121A	121B	121C	121D	121E	121F	121G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	590	590	590	590	590	590	590
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
<b>Conclusion</b>							

Specimen No.	121H	121I	121J	121K	121L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	590	590	590	590	590		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.049</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.100</b>
<b>Conclusion</b>						PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 38 of 70

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Flatware (Average of 12)	<b>0.189</b>	<b>0.226</b>
	Large Hollowware (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Small Hollowware (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Pitchers (Average of 12)	<b>0.049</b>	<b>0.100</b>

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 39 of 70

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	122A	122B	122C	122D	122E	122F	122G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	530	530	530	530	530	530	530
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
<b>Conclusion</b>							

Specimen No.	122H	122I	122J	122K	122L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	530	530	530	530	530		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.049</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.100</b>
<b>Conclusion</b>						PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 40 of 70

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Flatware (Average of 12)	<b>0.189</b>	<b>0.226</b>
	Large Hollowware (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Small Hollowware (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Pitchers (Average of 12)	<b>0.049</b>	<b>0.100</b>

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.





YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 41 of 70

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	123A	123B	123C	123D	123E	123F	123G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	560	560	560	560	560	560	560
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
<b>Conclusion</b>							

Specimen No.	123H	123I	123J	123K	123L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	560	560	560	560	560		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.049</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.100</b>
<b>Conclusion</b>						PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 42 of 70

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Flatware (Average of 12)	<b>0.189</b>	<b>0.226</b>
	Large Hollowware (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Small Hollowware (Average of 12)	<b>0.049</b>	<b>0.100</b>
	Pitchers (Average of 12)	<b>0.049</b>	<b>0.100</b>

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 43 of 70

**DETAILED RESULTS:****FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2011)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	120A	120B	120C	120D	120E	120F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	590	590	590	590	590	590		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS		

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	<b>0.5</b>	<b>0.5</b>
	Flatware (Average of 6)	<b>0.5</b>	<b>3.0</b>
	Large Hollowware (Any of 6)	<b>0.25</b>	<b>1.0</b>
	Small Hollowware (Any of 6)	<b>0.5</b>	<b>2.0</b>
	Pitchers (Any of 6)	<b>0.25</b>	<b>0.5</b>

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 44 of 70

**DETAILED RESULTS:****FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2011)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	121A	121B	121C	121D	121E	121F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	590	590	590	590	590	590		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	<b>0.5</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS		

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	<b>0.5</b>	<b>0.5</b>
	Flatware (Average of 6)	<b>0.5</b>	<b>3.0</b>
	Large Hollowware (Any of 6)	<b>0.25</b>	<b>1.0</b>
	Small Hollowware (Any of 6)	<b>0.5</b>	<b>2.0</b>
	Pitchers (Any of 6)	<b>0.25</b>	<b>0.5</b>

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 45 of 70

**DETAILED RESULTS:****Client's Requirement, Leachable Lead & Cadmium from Glassware and Ceramics – Lip & Rim**

Test Method: ASTM C927-80(2014)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	60A	60B	60C	60D	60E	60F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

Specimen No.	61A	61B	61C	61D	61E	61F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**Remark:**

The limit is quoted from Society of Glass &amp; Ceramic Decorated Products.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 46 of 70

**DETAILED RESULTS:****Client's Requirement, Leachable Lead & Cadmium from Glassware and Ceramics – Lip & Rim**

Test Method: ASTM C927-80(2014)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	62A	62B	62C	62D	62E	62F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

Specimen No.	63A	63B	63C	63D	63E	63F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**Remark:**

The limit is quoted from Society of Glass &amp; Ceramic Decorated Products.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 47 of 70

**DETAILED RESULTS:****Client's Requirement, Leachable Lead & Cadmium from Glassware and Ceramics – Lip & Rim**

Test Method: ASTM C927-80(2014)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	64A	64B	64C	64D	64E	64F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

Specimen No.	65A	65B	65C	65D	65E	65F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**Remark:**

The limit is quoted from Society of Glass &amp; Ceramic Decorated Products.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 48 of 70

**DETAILED RESULTS:****Client's Requirement, Leachable Lead & Cadmium from Glassware and Ceramics – Lip & Rim**

Test Method: ASTM C927-80(2014)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	66A	66B	66C	66D	66E	66F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

Specimen No.	67A	67B	67C	67D	67E	67F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**Remark:**

The limit is quoted from Society of Glass &amp; Ceramic Decorated Products.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.





YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 49 of 70

**DETAILED RESULTS:****Client's Requirement, Leachable Lead & Cadmium from Glassware and Ceramics – Lip & Rim**

Test Method: ASTM C927-80(2014)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	68A	68B	68C	68D	68E	68F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

Specimen No.	69A	69B	69C	69D	69E	69F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**Remark:**

The limit is quoted from Society of Glass &amp; Ceramic Decorated Products.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 50 of 70

**DETAILED RESULTS:****Client's Requirement, Leachable Lead & Cadmium from Glassware and Ceramics – Lip & Rim**

Test Method: ASTM C927-80(2014)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	70A	70B	70C	70D	70E	70F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

Specimen No.	71A	71B	71C	71D	71E	71F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**Remark:**

The limit is quoted from Society of Glass &amp; Ceramic Decorated Products.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 51 of 70

**DETAILED RESULTS:****Client's Requirement, Leachable Lead & Cadmium from Glassware and Ceramics – Lip & Rim**

Test Method: ASTM C927-80(2014)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	72A	72B	72C	72D	72E	72F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

Specimen No.	135A	135B	135C	135D	135E	135F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**Remark:**

The limit is quoted from Society of Glass &amp; Ceramic Decorated Products.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 52 of 70

**DETAILED RESULTS:****Client's Requirement, Leachable Lead & Cadmium from Glassware and Ceramics – Lip & Rim**

Test Method: ASTM C927-80(2014)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	136A	136B	136C	136D	136E	136F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

Specimen No.	137A	137B	137C	137D	137E	137F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**Remark:**

The limit is quoted from Society of Glass &amp; Ceramic Decorated Products.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 53 of 70

**DETAILED RESULTS:****Client's Requirement, Leachable Lead & Cadmium from Glassware and Ceramics – Lip & Rim**

Test Method: ASTM C927-80(2014)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	138A	138B	138C	138D	138E	138F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	200	200	200	200	200	200	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.4</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>4.0</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**Remark:**

The limit is quoted from Society of Glass &amp; Ceramic Decorated Products.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 54 of 70

**DETAILED RESULTS:****Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead in Surface Coating Materials**

Test Method: CPSC-CH-E-1003-09.1  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5	6+7+8	9+10+11	12+13	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	27	ND	ND	ND	ND	90
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	14	74+75	77+78+79	80+81+82	83+84	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	130+131	132+133	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	---	---	---	90
<b>Conclusion</b>	PASS	PASS	---	---	---	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 55 of 70

**DETAILED RESULTS:****Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content**

Test Method: ASTM F963-17 Clause 8.3.1  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5	6+7+8	9+10+11	12+13	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	27	ND	ND	ND	ND	<b>90</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	14	16+17+18	19+20+21	22+23	24+25	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	<b>90</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	41+42	43+44	53	54	74+75	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	<b>90</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

**Note:**

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 20 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 56 of 70

**DETAILED RESULTS:****Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content**

Test Method: ASTM F963-17 Clause 8.3.1  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	77+78+79	80+81+82	83+84	90	96+97+98	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	<b>90</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	99+100	130+131	132+133	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	---	---	<b>90</b>
<b>Conclusion</b>	PASS	PASS	PASS	---	---	

*Note:*

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 20 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.





YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 57 of 70

**DETAILED RESULTS:****Canadian Glazed Ceramics and Glassware Regulations SOR/2016-175, Leachable Lead and Cadmium from Ceramics and Glassware – Interior**

Test Method: ISO 6486-1:1999

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	120M	120N	120O	120P	120Q	120R	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	595	595	595	595	595	595	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.50</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.5</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	<b>0.50</b>	<b>0.5</b>
	Flatware (Any of 6)	<b>0.50</b>	<b>3.0</b>
	Large Hollowware (Any of 6)	<b>0.25</b>	<b>1.0</b>
	Small Hollowware (Any of 6)	<b>0.50</b>	<b>2.0</b>
	Pitchers (Any of 6)	<b>0.25</b>	<b>0.5</b>

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 58 of 70

**DETAILED RESULTS:****Canadian Glazed Ceramics and Glassware Regulations SOR/2016-175, Leachable Lead and Cadmium from Ceramics and Glassware – Interior**

Test Method: ISO 6486-1:1999

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	121M	121N	121O	121P	121Q	121R	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	595	595	595	595	595	595	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.50</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.5</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

*Note:*

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category	Leachable Cd (mg/L)	Leachable Pb (mg/L)
Cups and Mugs (Any of 6)	<b>0.50</b>	<b>0.5</b>
Flatware (Any of 6)	<b>0.50</b>	<b>3.0</b>
Large Hollowware (Any of 6)	<b>0.25</b>	<b>1.0</b>
Small Hollowware (Any of 6)	<b>0.50</b>	<b>2.0</b>
Pitchers (Any of 6)	<b>0.25</b>	<b>0.5</b>

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 59 of 70

**DETAILED RESULTS:****Canadian Glazed Ceramics and Glassware Regulations SOR/2016-175, Leachable Lead and Cadmium from Ceramics and Glassware – Interior**

Test Method: ISO 6486-1:1999

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	122M	122N	122O	122P	122Q	122R	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	535	535	535	535	535	535	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.50</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.5</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

**Note:**

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	<b>0.50</b>	<b>0.5</b>
	Flatware (Any of 6)	<b>0.50</b>	<b>3.0</b>
	Large Hollowware (Any of 6)	<b>0.25</b>	<b>1.0</b>
	Small Hollowware (Any of 6)	<b>0.50</b>	<b>2.0</b>
	Pitchers (Any of 6)	<b>0.25</b>	<b>0.5</b>

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 60 of 70

**DETAILED RESULTS:****Canadian Glazed Ceramics and Glassware Regulations SOR/2016-175, Leachable Lead and Cadmium from Ceramics and Glassware – Interior**

Test Method: ISO 6486-1:1999

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	123M	123N	123O	123P	123Q	123R	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	565	565	565	565	565	565	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	<b>0.50</b>
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	<b>0.5</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

*Note:*

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	<b>0.50</b>	<b>0.5</b>
	Flatware (Any of 6)	<b>0.50</b>	<b>3.0</b>
	Large Hollowware (Any of 6)	<b>0.25</b>	<b>1.0</b>
	Small Hollowware (Any of 6)	<b>0.50</b>	<b>2.0</b>
	Pitchers (Any of 6)	<b>0.25</b>	<b>0.5</b>

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 61 of 70

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Dull white coating	On inner wall (all 1625-25 styles)
2	Black coating	On outer wall (0011-87 BK/ 1625-25 BK styles)
3	Transparent coating	On outer wall (0011-87 SL style)
4	Blue coating	On outer wall (1625-25 BL style)
5	Dull black coating	On outer wall (1625-28 BK/ 1625-09 BK/ 1624-89 BK/ 1625-45 BK/ 1626-24 BK styles); band of body (all 1624-92 styles)
6	Dull blue coating	Lip & Rim of tumbler (1624-89 BK/ 1626-24 BK styles)
7	Brown coating	Lip & Rim of tumbler (1624-89 BL/ 1626-24 BL styles)
8	Red coating	Lip & Rim of tumbler (1624-89 RD/ 1626-24 RD styles)
9	Turquoise coating	On outer wall (1625-28 TQ style)
10	Dull brown coating	On outer wall (1625-09 COL/ 1626-25 COP styles)
11	Grey coating	On outer wall (1624-89 GA/ 1625-09 GA/ 1626-25 GA styles)
12	Green coating	On outer wall (1624-89 LM/ 1625-09 LM/ 1626-25 LM styles)
13	White coating	On outer wall (1624-89 WH/ 1626-25 WH/ 1625-80 WH/ 1626-24 WH styles)
14	Silvery coating	On main shell of speaker (all 1625-81 styles)
15	Black plastic (PP-co)	Lid (all 0011-87/ all 1625-25/ all 1625-81/ 1625-23 SL styles); neck of body (all 1625-25 styles); slider (1625-28 BK/ 1625-45 BK styles); holder of infuse (1625-23 SL style); lid (all 1626-43/ all 1624-92 styles); slider (all 1624-92 styles); inner lid (all 1625-93 styles)
16	Black plastic	Lid (all 0011-87/ all 1625-25/ all 1625-81/ 1625-23 SL styles); flip (all 0011-87/ 1625-25 BK styles); neck of body (all 1625-25 styles); slider (1625-28 BK/ 1625-45 BK styles); holder of infuse (1625-23 SL style); lid (all 1626-43/ all 1624-92 styles); slider (all 1624-92 styles); inner lid (all 1625-93 styles)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 62 of 70

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
17	Translucent blue plastic (PP-co)	Slider (1625-28 BL style)
19	Red plastic (PP-co)	Slider (1625-28 RD style)
20	Bright grey plastic (PP-co)	Slider (1625-28 SL style)
21	Translucent turquoise plastic (PP-co)	Slider (1625-28 TQ style)
22	Transparent plastic (AS)	Lid (all 1625-28/ all 1625-09/ all 1624-89/ all 1626-07/ all 1626-24 styles)
23	Clear plastic (Tritan)	Swivel (all 1625-09/ all 1624-89 styles); straw/ ring of straw (all 9987-13 styles)
24	Clear blue plastic (Tritan)	Body (1625-81 RYL style)
25	Clear black plastic (Tritan)	Body (1625-81 SM style)
26	Blue plastic	Flip (1625-25 BL style)
27	Grey plastic	Flip (1625-25 SL style)
28	Dark grey plastic	Button (1625-23 SL style)
29	Off black plastic	Inner gear of lid (1625-23 SL style)
30	Dull clear plastic	Handle (all 1625-81 styles)
31	Dull black plastic	Main shell of speaker (all 1625-81 styles)
32	Matt black plastic	Inner pin of plug of Micro USB (all 1625-81/ all 1625-93 styles)
33	White plastic	Inner pin of plug of USB (all 1625-81/ all 1625-93 styles)
34	Black PVC	Plug of USB (all 1625-81/ all 1625-93 styles)
36	Grey soft plastic	Button of speaker (1625-81 SM styles)
37	Dull grey soft plastic	Band of lid/ cover of socket of USB (1625-81 SM styles)
38	Dull black soft plastic	Wrapper of cable of USB (all 1625-81/ all 1625-93 styles)
39	Blue soft plastic	Band of lid/ cover of socket of USB (1625-81 RYL style)
40	Dull blue soft plastic	Button of speaker (1625-81 RYL style)
41	Black soft plastic (TPR)	Gasket of flip (all 0011-87/ all 1625-25 styles)
42	Red soft plastic (Silicone)	Gasket of lid (all 0011-87 styles)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 63 of 70

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
43	Matt black soft plastic (Silicone)	Gasket (1625-23 style)
44	Translucent soft plastic (Silicone)	Gasket (all 1625-25/ all 1625-28/ all 1625-09/ all 1624-89/ all 1625-81/ 1625-45 BK/ all 1624-92/ all 1626-07/ all 1626-24 styles)
46	Black soft plastic (TPR)	Gasket of flip (all 0011-87 styles)
47	Black soft plastic (TPR)	Gasket of flip (all 1625-25 styles)
48	Translucent soft plastic (Silicone)	Gasket (all 1625-25 style)
49	Translucent soft plastic (Silicone)	Gasket (all 1625-28/ all 1624-89 styles)
50	Translucent soft plastic (Silicone)	Gasket (all 1625-09/ 1625-45 BK styles)
51	Translucent soft plastic (Silicone)	Gasket (all 1625-81 styles)
52	Silvery metal (#304)	Inner wall (all 0011-87/ all 1625-25/ all 1625-28/ all 1625-09/ all 1624-89/ 1625-45 BK/ 1625-23 SL/ all 1626-25/ all 1626-43/ all 1625-80/ all 1625-93/ all 1626-07/ all 1626-24 styles); infuse (1625-23 SL style)
53	Silvery metal	Inner wall (all 0011-87/ all 1625-25/ all 1625-28/ all 1625-09/ all 1624-89/ 1625-45 BK/ 1625-23 SL/ all 1626-25/ all 1626-43/ all 1625-80/ all 1625-93/ all 1626-07/ all 1626-24 styles); infuse/ outer wall/ bottom (1625-23 SL style)
54	Dull silvery metal	Outer wall (all 0011-87/ all 1625-25/ all 1625-28/ all 1625-09/ all 1624-89/ 1625-45 BK/ all 1626-25/ all 1626-43/ all 1625-80/ all 1625-93/ all 1626-07/ all 1626-24 styles); bottom (all 1625-25/ all 1625-93 styles)
55	Matt silvery metal	Axis of flip (all 0011-87 styles)
56	Off silvery metal	Pin of plug of USB (all 1625-81/ all 1625-93 styles)
57	Flat silvery metal	Pin of plug of Micro USB (all 1625-81/ all 1625-93 styles)
58	Bright silvery metal	Hook of pin of plug of Micro USB (all 1625-81/ all 1625-93 styles)
60	Dull black printed dull silvery metal	Lip & Rim of tumbler (1625-09 BK style)
61	Dull blue printed dull silvery metal	Lip & Rim of tumbler (1625-09 BL style)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 64 of 70

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
62	Dull brown printed dull silvery metal	Lip & Rim of tumbler (1625-09 COP style)
63	Red printed dull silvery metal	Lip & Rim of tumbler (1625-09 RD style)
64	Grey printed dull silvery metal	Lip & Rim of tumbler (1625-09 GA style)
65	Green printed dull silvery metal	Lip & Rim of tumbler (1625-09 LM style)
66	Dull black printed dull silvery metal	Lip & Rim of tumbler (1624-89 BK style)
67	Dull blue printed dull silvery metal	Lip & Rim of tumbler (1624-89 BL style)
68	Red printed dull silvery metal	Lip & Rim of tumbler (1624-89 RD style)
69	Grey printed dull silvery metal	Lip & Rim of tumbler (1624-89 GA style)
70	Green printed dull silvery metal	Lip & Rim of tumbler (1624-89 LM style)
71	White printed dull silvery metal	Lip & Rim of tumbler (1624-89 WH/ 1626-24 WH styles)
72	Brown printed dull silvery metal	Lip & Rim of tumbler (1624-89 COP style)
74	Transparent lacquer	On lid (all 9987-12 styles)
75	Dull transparent coating	On holder (1033-06 WD style); handle (all 1624-92 styles)
76	Off black coating	On holder (1033-06 WD style)
77	Bright black coating	On outer wall (1626-25 BK/ 1625-80 BK styles)
78	Matt black coating	On outer wall (1626-43 BK style)
79	Matt blue coating	On outer wall (1626-43 BL style)
80	Dull green coating	On outer wall (1626-43 LM style)
81	Dull red coating	On outer wall (1626-43 RD style)
82	Shiny black coating	On outer wall (1625-93 BK style)
83	Transparent turquoise coating	On inner wall (1625-74 SGL style)
84	Transparent black coating	On inner wall (1625-74 SM style)
85	Flat black plastic	Main shell of speaker (1625-93 BK style)
86	Shiny grey plastic	Main shell of speaker (1625-93 SL style)
87	Transparent plastic	Outer lid (all 1626-25 styles)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.





YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 65 of 70

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
88	Clear plastic	Lid (all 1625-80/ all 1625-74 styles); outer wall/ bottom (all 1625-74 styles)
89	Brown printed pink soft plastic with brown textile backing	Strap of holder (1033-06 WD style)
90	Matt black soft plastic (Silicone)	Gasket/ hole of lid (9987-12 BK style); cover of socket of USB (1625-93 BK style); sleeve (9987-13 BK style)
91	Matt black soft plastic (Silicone)	Gasket/ hole of lid (9987-12 BK style)
92	Dull turquoise soft plastic	Gasket/ hole of lid (9987-12 MTGR style)
93	Matt blue soft plastic	Gasket/ hole of lid (9987-12 BL style)
94	Light grey soft plastic	Cover of socket of USB (1625-93 SL style)
95	Black printed dull white soft plastic	Button of speaker (all 1625-93 styles)
96	Matt blue soft plastic	Gasket/ hole of lid (9987-12 BL style); sleeve (9987-13 BL style)
97	Dull turquoise soft plastic	Gasket/ hole of lid (9987-12 MTGR style); sleeve (9987-13 MTGR style)
98	Off grey soft plastic (Silicone)	Gasket (all 1625-80 styles)
99	White soft plastic (Silicone)	Gasket/ loop of neck/ bottom (all 1625-74 styles); sleeve (9987-13 WH style); gasket/ hole of lid (9987-12 WH style)
100	Matt grey soft plastic (Silicone)	Gasket (all 1626-25/ all 1626-43/ all 1625-93 styles)
101	White soft plastic (Silicone)	Gasket (all 1625-74 styles); gasket/ hole of lid (9987-12 WH style)
102	Matt grey soft plastic (Silicone)	Gasket (all 1626-25 styles)
103	Matt grey soft plastic (Silicone)	Gasket (all 1626-43 styles)
104	White soft plastic (Silicone)	Gasket (all 1625-74 styles)
105	Translucent soft plastic (Silicone)	Gasket (all 1624-92 styles)
106	Matt grey soft plastic (Silicone)	Gasket (all 1625-93 styles)
107	Matt black soft plastic (Silicone)	Gasket (9987-12 BK style)
108	White soft plastic (Silicone)	Gasket (9987-12 WH style)
109	Dull turquoise soft plastic (Silicone)	Gasket (9987-12 MTGR style)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 66 of 70

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
110	Matt blue soft plastic (Silicone)	Gasket (9987-12 BL style)
111	Matt black soft plastic (Silicone)	Hole of lid (9987-12 BK style)
112	White soft plastic (Silicone)	Hole of lid (9987-12 WH style)
113	Dull turquoise soft plastic (Silicone)	Hole of lid (9987-12 MTGR style)
114	Matt blue soft plastic (Silicone)	Hole of lid (9987-12 BL style)
115	Shiny silvery metal	Top of lid (all 1626-25/ all 1625-80 styles)
116	Sharp silvery metal	Handle (all 1626-43 styles)
117	Shine silvery metal	Rivet of handle (all 1624-92 styles)
118	Rare silvery metal	Band of body (all 1624-92 styles)
119	Soft silvery metal	Outer lid/ main shell of speaker (all 1625-93 styles)
120	Black printed dull white ceramic	Interior of mug (1624-92 BK style)
121	White printed dull white ceramic	Interior of mug (1624-92 WH style)
122	Dull clear glass	Interior of bottle (all 1625-74 styles)
123	Matt clear glass	Interior of tumbler (all 9987-13 styles)
124	Dull clear glass	Interior of cup (1033-06 WD style)
125	Dull clear glass	Inner wall (all 1625-74 styles); cup (1033-06 WD style)
126	Matt clear glass	Whole of tumbler (all 9987-13 styles)
127	Black printed dull white ceramic	Whole of mug (1624-92 BK style)
128	White printed dull white ceramic	Whole of mug (1624-92 WH style)
129	Brown natural wood	Lid (all 9987-12 styles)
130	Dark grey coating	On outer wall (1626-07 BK style)
131	Off blue coating	On outer wall (1626-07 BL style)
132	Matt green coating	On outer wall (1626-07 LM style)
133	Matt red coating	On outer wall (1626-07 RD style)
134	Translucent soft plastic (Silicone)	Gasket (all 1626-07/ all 1626-24 styles)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



YOUR EYES IN THE SUPPLY CHAIN

Test Report #: 19H-002304(A1)

Page 67 of 70

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
135	Dark grey printed dull silvery metal	Lip & Rim of tumbler (1626-07 BK style)
136	Off blue printed dull silvery metal	Lip & Rim of tumbler (1626-07 BL style)
137	Matt green printed dull silvery metal	Lip & Rim of tumbler (1626-07 LM style)
138	Matt red printed dull silvery metal	Lip & Rim of tumbler (1626-07 RD style)

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.  
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
 This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**SAMPLE PHOTO:**



QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
*The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.*

**SAMPLE PHOTO:**



QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
*The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.*  
*The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.*  
*This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.*  
*ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.*

**SAMPLE PHOTO:**



-End Report-

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong ♦ Tel: (852)3185 8000.  
*The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.  
The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.  
This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.  
ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.*